


| | | | | | | | |
|-------------------------------|---------------------------------|----------|----------|----------|----------|----------|---|
| Ledertyp / Type: | Shoe upper full grain brilliant | | | | | |  <p>Floridsdorfer Hauptstr 29/5 A 1210 Vienna Tel: +43 1 278 13 57 Fax: +43 1 278 13 57 e-mail: dlh@dlh.at</p> |
| Farbe / Colour: | black | | | | | | |
| Nr.: / No.: | DLH - I 454 | | | | | | |
| Bemerkungen / Notes | | | | | | | |
| MATERIALIEN / PRODUCTS | AUFTRÄGE / APPLICATIONS | | | | | | ARBEITSWEISE / PROCESS |
| | 1 | 2 | 3 | 4 | 5 | 6 | |
| K-Pigment | 40 | 40 | | | | | 1) Polish coat 1-2x spray, polish |
| Ölgrund AK | 70 | 70 | | | | | |
| Wachstop FP | 230 | 230 | | | | | |
| Water | 400 | 400 | 400 | | | | 2) Bottom coat 1-2x spray, rotopress |
| Polyton WM874 | | 80 | 80 | | | | |
| Anilin extra | 20 | 20 | | | | | 1x spray |
| Penetrator DN | 70 | 70 | | | | | 3) Top coat 1x spray, rotopress |
| Polyton W 780 | | 100 | | | | | |
| Glanztop K | | 100 | 100 | | | | |
| Modifikator VP 391 | | 20 | 15 | | | | |
| Vernetzer A100 | | 2 | 2 | | | | |
| Glanztop W 267 | | | 100 | | | | |
| Hydrophobierung VP 757 | | | 20 | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |