

# E-Lack SW900

**Typ:** Wässriger und solvent verdünnter NC Lack

**Festkörper:** ca. 26%

**Flammpunkt:** > 61°C

**Type:** *water and solvent thinnable NC lacquer*

**Solid content:** *approx. 26%*

**Flashpoint:** *> 61°C*

**Eigenschaften:** E-Lack SW900 ist ein in Wasser emulgierbarer und mit Lösungsmittel verdünnter NC-Lack. Leder die mit E-Lack SW900 gefinisht werden weisen eine hohe Brillanz und sehr gute Echtheiten auf. Mit Lösungsmittel verdünnt (1:2 bis 1:3) ist der Glanz nochmals um eine Stufe höher. Für die Verwendung mit Wasser schlagen wir folgendes Rezept vor:

**Properties:** *E-Lack SW900 was developed for the usage in water and solvent systems. Leathers finishes with E-Lack SW900 show a high brilliance and guaranty excellent physical fastness. E-Lack SW 900 diluted with solvents achieves a one step higher gloss than emulsified with water. For the usage in water we recommend the following starting formulation:*

100 T E-Lack SW900	
25 T Wasser	gut mischen
25 T Wasser	gut mischen
250T Wasser	

100 parts E-Lack SW900	
25 parts water	<i>stir well</i>
25 parts water	<i>stir well</i>
250 parts water	

**Lagerung:** + 2°C to + 30°C  
frostempfindlich

**Storage:** +2°C to + 30°C  
*sensitive to frost*

**Lagerzeit:** 6 Monate  
in gut verschlossenem Gebinde.

**Shelf life:** 6 months  
*in well sealed containers.*

Vor Gebrauch gut aufrühren.

*Stir well before use.*