

Filler PL/1

Typ: Polymer Füllmittel
Festkörper: ca. 27%
pH-Wert: ca. 8,5

Type: Polymerisate filling agent
Solid content: approx. 27%
pH-value: approx. 8,5

Eigenschaften: Filler PL/1 basiert auf hochwertigen PU-Dispersionen und Füllmittel und wurde speziell als Grundierung von geschliffenen, sehr schlechten Ledersortimenten entwickelt. Filler PL/1 wird nach der unten angegebenen Richtrezeptur appliziert, getrocknet, konditioniert über ca. 8 Std., gebügelt mit min. 110°C (wenn möglich mit einer Sandplatte) und mit einem Papier Nr. 400 oder feiner nachgeschliffen. Die darauffolgende Zurichtung kann dann betriebsüblich erfolgen, zur Erreichung höchsten Qualitätsstandards empfehlen wir aber unsere DLH Compact Binder zur weiteren Beschichtung.

Richtrezeptur: 1000 T Filler PL/1
 10 T Vernetzer A100
 1x Roller Coater ca. 120g/m²

Properties: Filler PL/1 is based on high quality PU-dispersions and Fillers especially developed to be used as bottom coat on buffed and very low assortment leathers. Filler PL/1 should be applied according the formulation below. Very important is to follow exact procedure to achieve the right result. After drying the leather should rest for approx. 8 hours than plate with Rotopress at 110°C and buff again with paper no.400 or more fine... . The following finish can be house standard, but for best quality we recommend the DLH Compact resins for further coating.

Starting formulation: 1000 p. Filler PL/1
 10 p. water
 1x Roller Coater approx. 120g/m²

Lagerung: +2°C to +30°C
 frostempfindlich
 kein Gefahrgut

Lagerzeit: 6 Monate
 in gut verschlossenem Gebinde.

Vor Gebrauch gut aufrühren.

Storage: +2°C to +30°C
 sensitive to frost
 no dangerous good

Shelf life: 6 months
 in well sealed containers.

Stir well before use.

