

Hydrophobierung VP757

Typ: Fluorcarbonharz

Type: Fluor carbon resin

Festkörper: ca. 20%

Solid content: approx. 20%

pH-Wert: ca. 5

pH-value: approx. 5

Eigenschaften: Hydrophobierung VP757 wird mit Wasser verdünnt vor der Zurichtung aufgetragen. Nach dem Trocknen ist das Leder Wasser- und Öl-abweisend. Dadurch wird auch eine deutliche Verbesserung der Wassertropfenfestigkeit der gesamten Zurichtung erzielt. Im Bedarfsfall können auch bereits zugerichtete Leder mit der Hydrophobierung VP757 in Kombination mit unseren E-Lacken überspritzt werden.

Properties: Hydrophobierung VP757 is applied thinned with water before the finish. After drying the leather will be water and oil repellent. Such achieving a distinct improvement in water drop resistance for the completed finish. In case of need also already finished leathers can be sprayed with Hydrophobierung VP757 in combination with our E-lacquers.

Lagerung: +2°C to +30°C
frostempfindlich
kein Gefahrgut

Storage: +2°C to +30°C
sensitive to frost
no dangerous good

Lagerzeit: 6 Monate
in gut verschlossenem Gebinde.

Shelf life: 6 months
in well sealed containers.

Vor Gebrauch gut aufrühren.

Stir well before use.