

Ölgrund SW

Typ: Wachs-Lösungsmittel-
gemisch

Type: wax mixture
in solvents

Wirksubstanz: ca. 27%

Active substance: approx. 27%

Flammpunkt: 14°C

Flashpoint: 14°C

Eigenschaften: Ölgrund SW muß erwärmt (50-55°C) auf das Leder aufgetragen und nach gutem Austrocknen bei Raumtemperatur (ca. 22°C) heiß abgebügelt werden. Der auf geeignetem Leder erzielte Pull-up Effekt ist sehr wirkungsvoll und gut rückpolierbar. Kann in jedem Verhältnis mit Ölgrund SK gemischt werden.

Properties: Ölgrund SW produces on appropriate leathers a striking pull-up effect which may be well repolished. Prior to use Ölgrund SW must be warmed up to 50°-55°C and after good drying at room temperature the leathers have to be hot plated. Ölgrund SW can be mixed with Ölgrund SK in all ratio.

Lagerung: +2°C to +30°C
frostfest
flammbar
UN1993 ADR KI.3 Zi. 5b

Storage: +2°C to +30°C
frostproof
flammable
UN11993 ADR Cl.3 Cf.5b

Lagerzeit: 12 Monate
in gut verschlossenem Gebinde.

Shelf life: 12months
in well sealed containers.

Vor Gebrauch gut aufrühren.

Stir well before use.