

# Ölgrund SK

**Typ:** Wachs-Lösungsmittel-  
gemisch

**Type:** wax mixture  
in solvents

**Wirksubstanz:** ca. 25%

**Active substance:** approx. 25%

**Flammpunkt:** 50°C

**Flashpoint:** 50°C

**Eigenschaften:** Ölgrund SK ist auf ca. 50°C zu erwärmen und mittels Roller-Coater auf das Leder aufzutragen. Über Nacht getrocknet und heiß abgebügelt erhält man einen starken Pull-up Effekt mit guter Wassertropfenechtheit. Ölgrund SK kann in jedem Verhältnis mit dem weicher eingestellten Ölgrund SW gemischt werden.

**Properties:** Ölgrund SK produces a strong pull-up effect with good water resistance when applied by Roller Coater. Prior to use Ölgrund SK must be warmed up to approximately 50°C and after slowly drying at room temperature over night the leathers have to be hot plated the next day. Can be mixed in all ratio with the softer Ölgrund SW.

**Lagerung:** +2°C to +30°C  
frostfest  
flammbar  
UN1993 ADR KI.3 Zi. 31c

**Storage:** +2°C to +30°C  
frostproof  
flammable  
UN1993 ADR Cl.3 Cf.31c

**Lagerzeit:** 12 Monate  
in gut verschlossenem Gebinde.

**Shelf life:** 12months  
in well sealed containers.

Vor Gebrauch gut aufrühren.

Stir well before use.